

Specification Data: SRV Slip Test 4S Rubber (BS 7976-2:2002)

The following slip test results for Ecodek wood/polymer composite deck boards are as tested in February 2020 to BS7976-2: 2002. These tests have been done on clean boards. In order to maintain traction levels similar to these shown, it is imperative that the deck is designed so as to allow proper drainage and that the deck surface is kept as clean as possible.

Pendulum Test Value (4S Rubber)

Conditions	Board Condition	Signature AT	Signature HD	Heritage	Stadia	Peaks	Parks
Dry	New	53	56	47	54	55	65
Wet	New	30	31	39	34	40	59

Low Slip Potential	36+
Medium Slip Potential	25-35
High Slip Potential	0-24

Signature and Stadia

The grooved surface offers improved slip resistance over the ribbed surface. Although both sides of the board are classified as low potential for slip.

Heritage

The embossed woodgrain pattern allows a natural grip to the surface of the flat board.

Peaks and Parks

The 3- sided capping found in the Peaks and Parks range allows for the enhanced grain depth to be achieved, allowing for a superior Slip Test result.

The above results were achieved under laboratory testing conditions and are from samples picked at random. Because of the variable nature of the natural and recycled materials used in the manufacture of Ecodek, slip resistance results may vary slightly from batch to batch. When using Ecodek on a ramp or incline, we strongly recommend the use of anti-slip inserts as the potential for slip increases proportionally with angle of incline.