

# Technical data sheet

for Fascia board


Physical property	Test method	Value
Linear mass	EN 15534-1: 2014, 6.5	2.66 kg/m
Dimensions	EN 15534-1: 2014, 6.6.2	19 x 136 mm
Deviation from straightness	EN 15534-1: 2014, 6.6.3	0.16 mm
Cupping	EN 15534-1: 2014, 6.6.4	0.48 mm

Mechanical characteristics	Test method	Value
Falling mass impact resistance	EN 15534-1: 2014, 7.1.2.1 (EN 477: 1995)	0.18 mm
Ultimate tensile strength	EN 15534-1: 2014, 7.2 (EN ISO 527-2)	8.54 MPa
Elastic modulus (MOE)	EN 15534-1: 2014, 7.3.2 (EN 310: 1993)	2.60 GPa
Maximum stress (MOR)	EN 15534-1: 2014, 7.3.2 (EN 310: 1993)	29.88 MPa
Deflection at 500N	EN 15534-1: 2014, 7.3.2 (EN 310: 1993)	0.46 mm

Durability	Test method	Value
Moisture resistance under cyclic test conditions	EN 15534-1: 2014, 8.3.2 (EN 321: 2001)	Deflection at 250N = 0.40 mm
Swelling and water absorption	EN 15534-1: 2014, 8.3.1 (EN 317)	Thickness = 1.88% Width = 0.16% Length = 0% Weight = 1.16%

## For more details

-  01978 667840
-  [enquiries@ecodek.co.uk](mailto:enquiries@ecodek.co.uk)
-  [ecodek.co.uk](http://ecodek.co.uk)



Making outdoors, yours